

1 **(BSP December 2, 2002)**
2 **Curing Polyester Concrete**
3 Traffic and equipment shall not be permitted on the polyester overlay for at least
4 four hours and until the polyester overlay has reached a minimum compressive
5 strength of 3,000 psi as verified by the rebound number determined in accordance
6 with ASTM C 805.
7
8 Areas in the polyester concrete that do not totally cure, or that fail to attain the
9 minimum compressive strength specified above, shall be removed and replaced
10 with new polyester concrete material by the Contractor, at no additional expense to
11 the Contracting Agency.